



ATLANTIC HEAT TRANSFER FLUIDS

High Performance Heat Transfer Fluids

DESCRIPTION

ATLANTIC HEAT TRANSFER FLUIDS are high performance HTOs formulated from highly refined base stocks that are resistant to thermal cracking and chemical oxidation & are intended for use in closed indirect heating installations. The flash points of these oils will not decrease significantly in service because of their resistance to thermal cracking at the operating temperatures for which they are recommended.

APPLICATIONS

ATLANTIC HEAT TRANSFER FLUIDS are recommended for use in open and closed installations where the bulk oil temperature ranges are as outlined in the table below and where minimum shutdown temperatures are not below -7°C.

- Bulk Oil Temperature Ranges for ATLANTIC HTO 22: Closed Systems (-7°C to 285°C), Open Systems (-7°C to 150°C)
- Bulk Oil Temperature Ranges for ATLANTIC HTO 32: Closed Systems (-7°C to 315°C), Open Systems (-7°C to 180°C)
- Bulk Oil Temperature Ranges for ATLANTIC HTO 46: Closed Systems (-7°C to 335°C), Open Systems (-7°C to 200°C)
- Bulk Oil Temperature Ranges for ATLANTIC HTO 68: Closed Systems (-7°C to 345°C), Open Systems (-7°C to 210°C)
- Closed, cold-oil sealed, indirect heating and cooling systems in all kinds of industrial processes operating at bulk oil temperatures up to the maximum temperatures quoted in the table above and at atmospheric pressure.
- Open systems provided the bulk temperatures do not exceed the maximum temperatures quoted in the table above.

PROPERTIES

ATLANTIC HEAT TRANSFER FLUIDS are thermally stable and are capable of an extremely long service life without deposit formation or viscosity increase. They demonstrate specific heats and thermal conductivities that provide more rapid heat dissipation. They have good heat transfer efficiency and their viscosities are such that they can be pumped readily at both start-up and operating temperatures.

PERFORMANCE FEATURES AND BENEFITS

- Performance and reliability, even in severe applications.
- High resistance to thermal cracking and decomposition
- Good thermal and oxidative stability
- Excellent thermal properties
- Product integrity assurance through independent verification
- Improves operating efficiency of heat transfer system
- Maintains viscosity and film thickness at high temperatures to help protect equipment
- Freedom from sludge and coke deposits
- Good low temperature fluidity

RECOMMENDATIONS / SPECIFICATIONS

Meets or exceeds the requirements of: FDA 21 CFR 178.3570, DIN 51522 (1998 - 11), Classified as ISO 6743-12 Family Q

TYPICAL TECHNICAL PROPERTIES

PRODUCT CODE	IL-25004-1	IL-25004-2	IL-25004-3	IL-25004-4
ATLANTIC HTO	22	32	46	68
Density at 15°C, g/ml, ASTM D4052	0.843	0.851	0.853	0.865
Kinematic Viscosity at 40°C, mm ² /s, ASTM D445	20.2	29	46	68
Kinematic Viscosity at 100°C, mm ² /s, ASTM D445	4.2	5.1	6.7	8.7
Flash Point(COC), °C, ASTM D92, (min)	200	210	220	230
Pour Point, °C, ASTM D97	-24	-18	-15	-15
Micro-carbon Residue, (Conradson), wt %, ASTMD4530,(max)	0.05	0.05	0.05	0.05
Copper Strip Corrosion, 3 hrs @100°C, ASTM D 130 1A	1A	1A	1A	1A

Note: These characteristics are typical of current production. While future production will conform to Atlantic's specification, variations in these characteristics may occur.

ATL/PDS/IL/04-12570-71L/01*, 01.05.25, Page 1/1

* supersedes all previous versions

Packing: 18L, 20L, 25L, 200L, 205L, 208L, 210L